

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-306208

(43)Date of publication of application : 17.11.1998

(51)Int.Cl.

C08L 69/00
C08K 5/42
C08K 5/521
//C08L 69/00
C08L 27:18
C08L 33:10)

(21)Application number : 09-117963

(71)Applicant : MITSUBISHI ENG PLAST KK

(22)Date of filing : 08.05.1997

(72)Inventor : ISHII KAZUHIKO
NAKADA MICHIO

(54) POLYCARBONATE RESIN COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a polycarbonate resin composition, excellent in flame retardance and thermal stability and having a high impact strength.

SOLUTION: This polycarbonate resin composition is obtained by compounding 100 pts.wt. aromatic polycarbonate resin having 16,000-30,000 viscosity-average molecular weight with 0.5-40 pts.wt. phosphorus-based flame retardant, 0.01-5 pts.wt. polyfluoroethylene resin, 0.01-5 pts.wt. metal sulfonate and 0.5-30 pts.wt. multilayered structural polymer having an outermost shell layer composed of an alkyl (meth)acrylate-based polymer.